



Texdecor - Casamance
2, rue d'Hem
59780 WILLEMS
France

Your notice of
06-03-2024

Your reference

Date
04-04-2024

Analysis Report 24.01300.10


Required tests :

California Technical Bulletin 117 (2013)

| Sample id | Information given by the client | Date of receipt |
|-----------|---------------------------------|-----------------|
| T2404972 | 3347-3348-1242-3776-768 | 06-03-2024 |

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Samples

T2404972
3347-3348-1242-3776-768





Reference: T2404972 - 3347-3348-1242-3776-768

Section 1 : cover fabric test

Date of ending the test 27-03-2024
 Standard used ASTM E1353-08a (2013)
 Product standard California Technical Bulletin 117 (2013)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

Filling T 30130 (Recticel) - non-fire retardant foam
 Cover Sheeting Material Composition 100 % cotton - laundered weight (125 ± 28) g/m²

| | 1 | 2 | 3 |
|--|----------|----------|----------|
| Open flaming | no | no | no |
| Smoulders more than 45 min. | no | no | no |
| Vertical char length > 45 mm | no | no | no |

Test criteria

- no open flaming
- smouldering ≤ 45 minutes
- vertical char ≤ 45 mm

Requirements

- all specimens meet the test criteria → PASS
- two or more specimens fail the test criteria → FAIL
- one specimen fails the test criteria → 3 additional tests → PASS
- all specimens meet the test criteria

Conclusion

Pass